

# PLASTICIZER MFG. CO

# Trimenol

Tri octyl tri mellitate (T.O.T.M.)

## **Applications**

- \*Good for plastisols
- \*Good for methacrylate and NC.
- \*Interior automotive application
- \*automotive panel skins

### **Principal properties**

- \*Very low volatility
- \*Good resistance to extraction by soapy water

#### **Product data sheet**

Property	Rango	unit
Appearance	Light yellow oily liquid	
Molecular weight	547	gr.
Specific gravity @ 25°C	0.084-0.991	gr/ml
Ester content	99.0	PC
Acid value	0.2	mgKOH/rg
Color	100	Apha
Refractive index @20°C	1.4850-1.4870	
Boiling point	355	°C
Flash point	250	°C open cup
Water solubility @ 25°C	< 0.01	gr/l

**Packing:** 200Kgs. Net in new steel drums

**Storage:** this plasticizer can be kept in covered warehouse for 2 years

For more information please call +98 21 88702667