

Plasticizer Mfg. Co

TPU-620

Iso butylated urea formaldehyde resin

Delivery form 62% in iso butanol

Applications

*Recommended for stoving enamel

*Acid cure lacquer for woodfinishing

*Compatible with epoxy, acrylic, alkyd resins

Principal properties

*Excellent durability

*Resistance to heat and chemicals

Product data sheet

Property	Rango	unit
Solid content	62±2	PC
Viscosity@ 25°C	15-20	Stoks
Acid value	<10	mgKOH/gr
Solvent	iso butanol	
Etherified with	iso butyl	
Color	<3	Gardner
Reactivity	Medium	

Packing: 200Kgs. Net in steel drums

Storage: this U/F resin can be kept in covered warehouse for 18 months at 5-30°C

For more information please call +98 21 88702667